



## Zinc Octoate

The product preserves the film in "open" form, what favors curing of the whole film layer in the volume, so that its hardness improves. It also prevents the effect of film shrinkage and increases stability of the primary drier; the use as a dispersing agent is possible.

### Packing:

200 kg polyethylene barrels, or, by agreement with the customer, containers, which do not deteriorate the properties of the material

Guarantee period of storage - 6 months

### Quality data

in accordance with TU 2311-004-46913378-2004:

Zn, %	12 ± 0,2
Appearance	Transparent, homogeneous liquid with suspensions and precipitate
Mass fraction of non-volatile substances, %, not more than	67
Compatibility with white spirit	No separation and precipitation, opalescence is allowed
Color or chromaticity according to iodometric scale, mg I <sub>2</sub> /cm <sup>3</sup> , not more than	2