



Zirconium Octoate

The product is an alternative to lead drier but it is less toxic. It favors the film strength. It is used in combination with driers of cobalt, manganese and calcium. It is used in varnish and paint materials, where application of lead compounds is not permissible.

Packing:

200 kg polyethylene barrels, or, by agreement with the customer, containers, which do not deteriorate the properties of the material

Guarantee period of storage - 6 months

Quality data

in accordance with TU 2311-004-46913378-2004:

The content of Zirconium, Zr, %	18 ± 0,4	24 ± 0,5
Appearance	Homogeneous liquid without precipitate and foreign admixtures	
Mass fraction of non-volatile substances, %, not more than	62	80
Solubility with white spirit	No separation and precipitation, opalescence is allowed	
Color or chromaticity according to iodometric scale, mg I ₂ /cm ³ , not more than	Liquid of light color (yellow tint is possible)	